

POLYPRIME EP

Solvent free epoxy resin primer and sealer

POLYPRIME EP is a two component solvent free epoxy resin based primer and sealer for epoxy and polyurethane based coatings and toppings. POLYPRIME EP can also be applied as a scratch coat with the addition of graded quartz sand.

CHARACTERISTICS

- ▶ Solvent free
- ▶ Low viscosity
- ▶ Easy to apply by brush, roller, squeegee, airless spray
- ▶ Colorless

1 FIELDS OF APPLICATION

- ▶ Epoxy and polyurethane resin based car park coatings and toppings
- ▶ Epoxy and polyurethane resin based wall & floor coating
- ▶ Epoxy and polyurethane resin based self leveling system
- ▶ Epoxy and polyurethane based screeds
- ▶ As a scratch coat for floors after mixing with graded quartz sand

APPLICATION INSTRUCTIONS

Surface preparation

Ensure that the concrete floor is 28 days old and the surface moisture content less than 5% prior to the application of the primer. Clean the surface of all dust, dirt, degradable type of curing compound, oil and grease, cement laitance and other contaminants which will affect the bonding. Captive/shot blasting and grinding of the concrete surface is recommended for cleaning the surface. Cracks, blow holes and surface imperfections should be repaired with POLYPOXY BF* or THOMSIT RS 88* repair mortar. For larger areas, a scratch coat can be applied. The scratch coat can be prepared by mixing POLYPRIME EP with Aggregate No. 8. The scratch coat can be applied by a notched trowel.

Mixing

Pour Part B into the Part A pail and mix thoroughly with a mixing paddle for 1-2 minutes till a homogenous and uniform consistency is achieved. It is always recommended to mix a complete kit at a time. However, for small areas, part mixing may be carried out by employing proper weight measures.

Application

The mixed primer shall be applied within the working time of the product. The primer may be applied by brush, roller or squeegee. POLYPRIME EP shall be applied at a coverage rate of 4-5 m²/L. The coating is applied when the primer is dry. However, in all circumstances, the coating shall be applied within 24 hours of application of the primer. If the primer surface is left open for more than 24 hours, then a fresh coat of primer has to be re-applied.

COVERAGE

Smooth Finish 5m²/L

CLEANING

Clean all equipments with POLYSOLVENT immediately after use. Hardened materials can be removed mechanically only.

STORAGE & SHELF LIFE

Store the material in a cool, covered dry place. Do not expose the pails to direct sunlight and keep away from all sources of heat. In tropical climatic conditions, the product has to be stored in an air-conditioned environment and protected from high humidity. The shelf life of the product is 12 months in unopened condition if stored as per the recommendations. Exposure to high temperature and humidity will result in considerable deterioration of the product and reduce its shelf life.

HEALTH & SAFETY

As with all construction chemical products, caution should always be exercised. Protective clothing such as rubber gloves, safety goggles and face mask should be worn when handling the product. Treat any splashes to the skin or eyes with copious amount of fresh water. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

SUPPLY

POLYPRIME EP	5L & 15L kit
POLYPOXY BF	3kg kit
THOMSIT RS 88	25kg bag
Aggregate No. 8	25kg bag
POLYSOLVENT	5L & 20L pails

* Refer to website for TDS

TECHNICAL SPECIFICATION

PROPERTIES	VALUES
Color	Amber
Solid content, [%]	100
Density, [g/cc]	1.05±0.05
Application life [mins]	30
Initial cure [hrs]	6-8
Bond strength	Greater than the cohesive strength of concrete
Application temp, [°C]	5 to 35

All values given are subject to 5-10% tolerance

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards. The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23°C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

Manufactured in G.C.C.



Henkel Polybit Industries Ltd.
P.O. Box 293, Umm Al Quwain, UAE
Tel: +971 6 7670777, Fax: +971 6 7670197
henkelpolybit@henkelpolybit.com

Henkel Polybit Industries Ltd.
P.O. Box 2230, Al Khobar 31952, KSA
Tel: +966 13 808 4061/62, Fax: +966 13 812 1164
dammam@henkelpolybit.com