

DECORATIVE COATINGS

TECHNICAL DATA SHEET

NATIONAL TENNIS COURT TOPCOAT

DESCRIPTION	A high quality, alkali resistant acrylic co-polymer based paint. It is tough
	and abrasion resistant, National Tennis Court also contains antifungal and antibacterial additives.
RECOMMENDED USE	Used as a Tennis Court Paint, Car Parking and floor paint.

TECHNICAL DATA

COLOURS	As Per National Shade Card
FINISH	Matt
VOLUME SOLIDS	$40 \pm 2\%$
SPECIFIC GRAVITY KG/L	1.40 ± 0.05
THEORETICAL SPREADING RATE	8 M ² /LTR
RECOMMENDED (DFT) - MICRONS	50 per coat
RECOMMENDED (WFT) - MICRONS	125 per coat
DRYING TIME @ 30°C	Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.
	Touch dry (hours) : 1
	Dry to recoat (hours) : 2 - 4

APPLICATION DATA

APPLICATION METHOD	Brush, Roller or Spray
THINNING (VOLUME)	10 - 15% depending on the method of application
THINNER / CLEANER	Water
AIRLESS SPRAY REQUIREMENTS	Pressure / Tip Size : 2100 psi / 0.018" - 0.021"
CONV. SPRAY REQUIREMENTS	Atomizing Pressure : 50 psi
MIXING RATIO (VOLUME)	NA
POT LIFE @ 30°C	NA
RECOMMENDED SYSTEM	- National PVA Primer Sealer (or) : 1 coat
	- National PVA Primer White : 1 coat
	- National Tennis Court Topcoat : 2 coats

MISCELLANEOUS DATA

FLASH POINT	Water Base
SHELF LIFE @ 30°C	18 months in original sealed containers, with proper storage conditions.

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details, refer specifier and safety data.

