

**DECORATIVE COATINGS**

**TECHNICAL DATA SHEET**

**NATIONAL MINITEX (TEXTURED COATING)**

|                        |   |
|------------------------|---|
| <b>DESCRIPTION</b>     | A Copolymer emulsion based containing quartz aggregate giving a light textured, tough, weather resistant and flexible decorative finish. It can be overcoated with Nationalthane, National Polyurethane or Acrylic Rock topcoats. National Minitex contains antifungal and antibacterial additives. |
| <b>RECOMMENDED USE</b> | Texture coating for interior and exterior surfaces of concrete, plaster, masonry, brick work, gypsum, asbestos and wood.  |

**TECHNICAL DATA**

|                                    |   |
|------------------------------------|---|
| <b>COLOURS</b>                     | As Per National Shade Card  |
| <b>FINISH</b>                      | Matt / Light textured   |
| <b>VOLUME SOLIDS</b>               | 62 ± 2%   |
| <b>SPECIFIC GRAVITY KG/L</b>       | 1.72 ± 0.05   |
| <b>THEORETICAL SPREADING RATE</b>  | 3 M <sup>2</sup> /LTR (depends on Texture & Surface)  |
| <b>RECOMMENDED (DFT) - MICRONS</b> | 200 per coat  |
| <b>RECOMMENDED (WFT) - MICRONS</b> | 320 per coat  |
| <b>DRYING TIME @ 30°C</b>          | Temperature, humidity, air movement, film thickness and number of coats all affect the drying time. |
|                                    | Touch dry (hours) : 2 - 3   |
|                                    | Dry to recoat (hours) : 6 - 8   |
|                                    | Overcoating with any topcoat (hours) : Min. 24  |

**APPLICATION DATA**

|                              |   |
|------------------------------|---|
| <b>APPLICATION METHOD</b>    | Brush, Roller or Spray  |
| <b>THINNING (VOLUME)</b>     | Ready for use, if required add 5 - 10% water  |
| <b>THINNER / CLEANER</b>     | Water   |
| <b>MIXING RATIO (VOLUME)</b> | NA  |
| <b>POT LIFE @ 30°C</b>       | NA  |
| <b>RECOMMENDED SYSTEM</b>    | - National PVA Primer Sealer (or) National Acrylic Primer( W.B.) : 1 coat<br>(or)<br>- National Tex Primer : 1 coat<br>- National Minitex (Textured Coating) : 1 coat |

**MISCELLANEOUS DATA**

|                          |  |
|--------------------------|--|
| <b>FLASH POINT</b>       | Water Base   |
| <b>SHELF LIFE @ 30°C</b> | 18 months in original sealed containers, with proper storage conditions. |

**NOTE :** We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details, refer specifier and safety data.