



## TECHNICAL SPECIFICATIONS

### DECORATIVE COATINGS

### TECHNICAL DATA SHEET

<b>NATIONAL CAMOUFLAGE</b>
----------------------------

<b>DESCRIPTION</b>	A special alkyd based, camouflage enamel. It forms a tough film giving weather resistant flat finish, with good resistance to infra-red radiation.
<b>RECOMMENDED USE</b>	Protection of structural steel, heavy equipments, vehicle, etc. especially for defence purpose.

### TECHNICAL DATA

<b>COLOURS</b>	Special colours available on request.
<b>FINISH</b>	Smooth, Matt
<b>VOLUME SOLIDS</b>	55 ± 2%
<b>SPECIFIC GRAVITY KG/L</b>	1.50 ± 0.05
<b>THEORETICAL SPREADING RATE</b>	18 - 14 M <sup>2</sup> /LTR
<b>RECOMMENDED (DFT) - MICRONS</b>	30 - 40 per coat
<b>RECOMMENDED (WFT) - MICRONS</b>	55 - 75 per coat
<b>DRYING TIME @ 30°C</b>	Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.
	Touch dry (hours) : 1 - 2
	Dry to recoat (hours) : 8 - 12
	Hard dry (hours) : 18

### APPLICATION DATA

<b>APPLICATION METHOD</b>	Brush, Roller or Spray
<b>THINNING (VOLUME)</b>	5 - 10% depending on the method of application
<b>THINNER / CLEANER</b>	National G.P. Thinner
<b>AIRLESS SPRAY REQUIREMENTS</b>	Pressure / Tip size : 2200 psi / 0.015" - 0.020"
<b>CONV. SPRAY REQUIREMENTS</b>	Atomizing Pressure : 50 psi
<b>MIXING RATIO (VOLUME)</b>	Base : Hardener : NA
<b>POT LIFE @ 30°C</b>	NA
<b>RECOMMENDED SYSTEM</b>	- National Red Oxide Primer : 1 coat
	- National Camouflage Enamel : 1 coat

### MISCELLANEOUS DATA

<b>FLASH POINT</b>	38°C
<b>SHELF LIFE @ 30°C</b>	18 months in original sealed containers, with proper storage conditions.

**NOTE :** We warrant only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details, refer specifier and safety data.