

**TECHNICAL SPECIFICATIONS**
**DECORATIVE COATINGS**
**TECHNICAL DATA SHEET**
**NATIONAL TEXO COMPOUND**

<b>DESCRIPTION</b>	A coating, specially formulated to give a textured surface by spray application. It is based on high quality Copolymer emulsion containing fine quartz aggregate giving a light/medium/heavy textured tough, weather resistant, flexible decorative finish. It contains antifungal and antibacterial additives.
<b>RECOMMENDED USE</b>	Intermediate textured coating used in National Tile, National Acrylic Rock & National Eco System. Suitable for concrete, plaster, wood, etc.

**TECHNICAL DATA**

<b>COLOURS</b>	Off White
<b>FINISH</b>	Matt, light, medium & heavy textured
<b>VOLUME SOLIDS</b>	45 ± 2%
<b>SPECIFIC GRAVITY KG/L</b>	1.70 ± 0.05
<b>THEORETICAL SPREADING RATE</b>	2 - 1 M <sup>2</sup> /LTR
<b>RECOMMENDED (DFT) - MICRONS</b>	250 - 500 per coat
<b>RECOMMENDED (WFT) - MICRONS</b>	550 - 1100 per coat
<b>DRYING TIME @ 30°C</b>	Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.
	Touch dry (hours) : 4 - 6
	Dry to recoat (hours) : 24
	Overcoating with any topcoat (hours) : Min. 24

**APPLICATION DATA**

<b>APPLICATION METHOD</b>	Special Spray Gun
<b>THINNING (VOLUME)</b>	Ready for use
<b>THINNER / CLEANER</b>	Water
<b>SPRAY REQUIREMENTS</b>	Tip 0.197" - 0.315"
	Atomizing Pressure : 60 - 70 psi
<b>MIXING RATIO (VOLUME)</b>	Base : Hardener : NA
<b>POT LIFE @ 30°C</b>	NA
<b>RECOMMENDED SYSTEM</b>	- National PVA Primer White for Masonry (or) : 1 coat
	- National Tex Primer (or) National Acrylic Primer (W.B.) : 1 coat
	- National Texo Compound : 1 coat
	- National Acrylic Rock Topcoat : 2 coats

**MISCELLANEOUS DATA**

<b>FLASH POINT</b>	Water Base
<b>SHELF LIFE @ 30°C</b>	18 months in original sealed containers, with proper storage conditions.

**NOTE :** We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details, refer specifier and safety data.