

### **DECORATIVE COATINGS**

### TECHNICAL DATA SHEET

# NATIONAL GUARD PRIMER WHITE

DESCRIPTION	A two pack Epoxy Primer providing excellent water and chemical resistance. It has very good sealing properties.
RECOMMENDED USE	<ul> <li>- Primer for Epoxy textured coating.</li> <li>- General Purpose Primer for Epoxy system on concrete, masonry and wooden surfaces.</li> </ul>

### TECHNICAL DATA

COLOURS	White			
FINISH	Smooth, Matt			
VOLUME SOLIDS	$56 \pm 2\%$			
SPECIFIC GRAVITY KG/L	$1.62 \pm 0.05$ (mixed	d)		
THEORETICAL SPREADING RATE	14 M <sup>2</sup> /LTR			
RECOMMENDED (DFT) - MICRONS	40 per coat			
RECOMMENDED (WFT) - MICRONS	70 per coat			
DRYING TIME @ 30°C	Temperature, humidity, air movement, film thickness and			
	number of coats all affect the drying time.			
	Touch dry	(hours)	:	5 - 6
	Dry to recoat	(hours)	:	12 - 36
	Fully cured	(days)	:	7

## APPLICATION DATA

APPLICATION METHOD	Spray, Roller or Brush		
THINNING (VOLUME)	10 - 20% depending on the method of application		
THINNER / CLEANER	National Epoxy Thinner		
AIRLESS SPRAY REQUIREMENTS	Pressure / Tip Size : 2200 psi / 0.015" - 0.018"		
CONV. SPRAY REQUIREMENTS	Atomizing Pressure : 50 psi		
MIXING RATIO (VOLUME)	Base: Hardener : 4:1 (Mix thoroughly and allow the mixed paint to		
	mature for 15-20 mins. before use)		
POT LIFE @ 30°C	6 hours		
RECOMMENDED SYSTEM	- National Guard Primer White 1 coats		
	- National Guard Topcoat 2 coats		

## MISCELLANEOUS DATA

FLASH POINT (MIXED)	25°C
SHELF LIFE @ 30°C	18 months in original sealed containers, with proper storage conditions.

**NOTE:** We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details, refer specifier and safety data.

