AL-JAZEERA EGGSHELL

JA-16035

DESCRIPTION:

An ideal high quality silky emulsion paint based on acrylic resins, which is specially designed for exterior and interior applications in all weather conditions. It has a very good flow and gives smooth durable eggshell finish.

RECOMMENDED USE:

Recommended to use as a final coat with smooth touch for exterior and interior applications on concrete, cement, gypsum and brick surfaces.

CHARACTERISTICS:

- "Al-Jazeera Eggshell " has the following features:
- -Resists different weather conditions.
- -Excellent washability with water and detergent.
- -Very good adhesion, flow and leveling.
- -Very good color retention property.
- -Good water, alkali and salt resistance.
- -Eggshell finish with smooth touch.
- -Very Low VOC (Volatile Organic Components).
- -Formulated without formaldehyde, APEO and ammonia.

CERTIFICATES:

- -Certificated by Green Seal
- -Tested and approved by Dortmund University of VOC contents.

PHYSICAL CONSTANTS:

Finish: Eggshell finish.

Gloss: (5 - 7) at an angle of 60°, ASTM D523.
Colour: Produced in white and other colours

of "Al-Jazeera Paints" Colour card.

Specific Gravity: 1.30 At temperature of 25°C. ASTM

D1475.

Viscosity: 97 KU at temperature of 25°C. ASTM

D562.

Volume Solid: 40.4 %. ASTM D2697. D.F.T.: 40 μ , each coat.

Theoretical Spreading

Rate: $10.1 \text{ m}^2/\text{L}, \text{D.F.T- } 40 \text{ } \mu \text{ } (405 \text{ft}^2/\text{US})$

gallon)To avoid waste, be sure to buy the right amount of the paint for the

surface area required).

Water Resistance: Pass, ASTM D870.

Alkali Resistance: Pass, (NaOH solution), ASTM D1308.

Adhesion: Pass, ASTM D7234. Flexibility: Pass, ASTM D522.

Freeze-Thaw Stability: Pass, 3 cycles, ASTM D2243.

Storage Stability: Pass, 30 days at 52°C.(ASTM D1849) VOC: 33 g/ltr*(@ 280°C) ISO 11890 - 2:2012 .

SURFACE PREPARATION:

New surfaces

- -All new surfaces must be cured at least for 30 days prior to application of the primer.
- -The surface must be treated by removing all forms release and protrusions to get a suitable surface for application.

For previously painted surfaces:

- Remove old paint from surfaces completely.
- -Make sure that the surface is clean , \mbox{dry} , free from dust, oil, grease, salt and mold.
- -Fill the holes and cracks with suitable fillers "Al-Jazeera Crack Filler" prior to application of the primer.

APPLICATION GUIDE:

- 1.The surface must be removed from dust, grease, oil and other contaminants completely.
- 2.Surface temperature required during application must not be less than 10°C; the surface moisture should not exceed 8% and the relative humidity at work place not to exceed 70%.
- 3.Maximum pH of 9.
- 4. Paint should be stirred carefully before use.
- 5.A suitable quantity of water can be added to get reasonable viscosity for application.
- 6.Do not apply on wet and moistened surfaces until get completely dry.
- 7.Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be given between the two coats.
- 8. Adequate ventilation should be provided during drying time.

APPLICATION TOOLS:

Airless spray: Excalibur

Nozzle Orifice: "0.017-0.021" Nozzle Pressure: 15 MPa (2100psi)

Spray Angle: 40-60°

Spray gun: Recommended nozzle size: (1.5 – 1.8) mm.
 Roller: Recommended type: Soft and smooth

woolen roller.

•Brush. : General / Normal type.

THINNER:

Recommended thinner is "Tap Water".

THINNING RATIO:

-(0 - 5) % by volume for airless spray applications.
-(15 - 20) % by volume for spray gun applications.
-(10 - 15) % by volume for roller & brush applications.
Depends on the weather conditions at work place.

PAINTING SYSTEM:

For exterior surfaces:

- -Apply one coat of "Al-Jazeera Primex" or any other suitable type of Al-Jazeera primers, depending on surface and leave for full dry.
- -Apply two coats of "Al-Jazeera Eggshell".

For interior surfaces:

- -Apply one coat of "Al-Jazeera Primex" or any other suitable type of Al-Jazeera primers and leave for full dry.
- type of Al-Jazeera primers and leave for full dry.

 -Apply two coats of "Al-Jazeera Easy Putty". Then sand the
- surfaces with sanding paper and clean the dust coming from the sanding by a dry cloth or an air blower.
- -Apply two coats of "Al-Jazeera Eggshell".

DRYING TIME:

Surface dry: 30 min.
Full dry 4 hours.
Recoating interval 8 hours.(minimum)
All above results according to ASTM D5895 @25°C .

CLEANING TOOLS:

Tap water.

*Test report available on request.

Issued 2013 —

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Al-Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Al-Jazeera TSD, he should take his accountability in this connection.





AL-JAZEERA EGGSHELL

JA-16035

PACKING:

1 US Gallon - (Net : 3.6 Ltr). 20 Ltrs. Drum - (Net : 18 Ltr).

SHELF LIFE:

In sealed container: 12 months in a dry, cool and well -ventilated place.

SAFETY PRECAUTIONS:

During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided. When working with paint in in-sufficient ventilated areas, forced ventilation should be provided. For spray application system, eye, skin, respiratory protection are always recommended. Keep away from the reach of children.

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

*Test report available on request.