

### DESCRIPTION:

A water-borne decorative paint, based on a special type of effect pigment and pure acrylic emulsion to create a desert effect.

### RECOMMENDED USE:

Recommended to be used for interior application as a finish coat over "Al-Jazeera Rawa Primer" on concrete, cement and gypsum surfaces. The places where this product can be applied are palaces, offices, showrooms, hotels, restaurants, galleries etc.

### CHARACTERISTICS:

- "Al-Jazeera Rawa" has the following features:
- The effect of this unique paint resembles sand mountains in desert making this product special.
  - Turns living spaces into a master showpiece.
  - Very good adhesion and high durability properties.
  - APEO, formaldehyde and ammonia free.
  - Wide range of colors.

### PHYSICAL CONSTANTS:

Finish:	Metallic
Color:	Available as per Al-Jazeera Rawa catalog.
Specific Gravity:	1.05±0.03 at a temperature of 30±2°C. ASTM D1475.
Viscosity:	95±2KU at a temperature of 30±2°C. ASTM D562
Theoretical Spreading Rate:	4-5 m <sup>2</sup> /ltr (per coat).
Heater Stability:	Pass 49 days at 50°C.

### SURFACE PREPARATION:

- New surfaces:**
- All new surfaces must be cured at least for 30 days prior to application of the primer.
  - The surface must be treated by removing all forms release and protrusions to get a suitable surface for application.
- For previously painted surfaces:**
- Remove old paint from surfaces completely.
  - Make sure that the surface is clean, dry, free from dust, oil, grease, salt and mold.
  - Fill the holes and cracks with suitable fillers "Al-Jazeera Crack Filler" prior to application of the primer.

### APPLICATION GUIDE:

- 1.The surface must be removed from dust, grease, oil and other contaminants completely.
- 2.Surface temperature required during application must not be less than 10°C; the surface moisture should not exceed 8% and the relative humidity at work place not to exceed 70%.
- 3.Maximum pH of 9.
- 4.Paint should be stirred carefully before use.
- 5.Do not apply on wet and moistened surfaces until get completely dry.
- 6.During application coat must be taken to distribute product evenly over the surface.
- 7.Adequate ventilation should be provided during drying time.

### APPLICATION TOOLS:

Brush: Special type

### THINNER:

Not recommended.

### THINNING RATIO:

Not recommended.

### PAINTING SYSTEM:

- Apply one coat of "Al-Jazeera Primex" or any other suitable type of Al-Jazeera primer depending on surface and leave for full dry.
- Apply two coats of "Al-Jazeera Easy Putty" and Let it get full dry.
- Apply two coats of "Al-Jazeera Rawa Primer", of the same color as that of "Al-Jazeera Rawa" (topcoat), by using a fine roller or spray gun and make sure that surface is uniform and there are no roller marks.
- The color of "Al-Jazeera Rawa Primer" must always be the same as "Al-Jazeera Rawa" (topcoat).
- Apply one coat of product obliquely or horizontally in zigzag movement with the help of special recommended brush.

### DRYING TIME:

Surface dry	(15 - 20) minutes.
Full dry	5 hours.
Hard dry	24 hours.

All above test results according to ASTM D5895@25°C.

### CLEANING TOOLS:

Fresh water.

### PACKING:

Plastic container : 3 liters.

### SHELF LIFE:

In sealed container: 12 months in a dry, and well-ventilated place.

### SAFETY PRECAUTIONS:

During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided. When working with paint in insufficient ventilated areas, forced ventilation should be provided. For spray application system, eye, skin, respiratory protection are always recommended. Keep away from the reach of children.

For environmental safety, please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

**Note:** Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.