



- ❶ Joints waterproofing: According to Construction Joint Detail – Walls or Slabs.
- ❷ Strips Sealing: Clean pre-formed reglet thoroughly. Apply one slurry coat of PENETRON® to reglet at the rate of  $0.8 \text{ kg/m}^2$  ( $1.5 \text{ lbs/y}^2$ ). Fill reglet with PENECRETE™ in mortar consistency.
- ❸ PENETRON® slurry application: Apply PENETRON® slurry to the surface of elevator pit as indicated in 2 coats at  $1.4\text{-}1.6 \text{ kg/m}^2$  ( $2.5\text{-}3.0 \text{ lbs/y}^2$ ) in total.

Notes: Schematic diagram shows PENETRON® application only and does not depict the standard requirements for waterstops or expansion joint sealant.