



- ❶ Tank waterproofing: Apply PENETRON® slurry on the surface of tank as indicated in 2 coats at  $1.4\text{-}1.6\text{ kg/m}^2$  ( $2.5\text{-}3.0\text{ lbs/y}^2$ ) in total.
- ❷ Slab waterproofing: Apply PENETRON® slurry on the surface of lean concrete as indicated in 2 coats at  $1.4\text{-}1.6\text{ kg/m}^2$  ( $2.5\text{-}3.0\text{ lbs/y}^2$ ) in total.

**Notes:** Schematic diagram shows PENETRON® application only and does not depict the standard requirements for waterstops or expansion joint sealant.