



- ❶ Joints waterproofing: Clean joint thoroughly. Between pours, apply PENETRON® slurry to joint surfaces at $1.4\text{--}1.6\text{ kg/m}^2$ ($2.5\text{--}3.0\text{ lbs/y}^2$).
- ❷ Strips Sealing: Clean pre-formed reglet thoroughly. Apply one slurry coat of PENETRON® to reglet at the rate of 0.8 kg/m^2 (1.5 lbs/y^2). Fill reglet with PENECRETE™ in mortar consistency.
- ❸ PENETRON® slurry application: Coat the entire repair area with PENETRON® slurry extending 250mm (10in) beyond either side of the repair.

Notes:

- Horizontal construction joint of wall should not be designed in the interface between wall and slab, but within the wall above the slab.
- Schematic diagram shows PENETRON® application only and does not depict the standard requirements for waterstops or expansion joint sealant.