



- ❶ Clean pre-formed reglet thoroughly. Apply one slurry coat of PENETRON® to reglet at the rate of  $0.8 \text{ kg/m}^2$  ( $1.5 \text{ lbs/y}^2$ ). Fill reglet with PENECRETE™ in stiff consistency and pack tightly.
- ❷ PENETRON® slurry application: Coat the entire repair area with PENETRON® slurry extending 250mm (10in) beyond either side of the repair.

**Notes:**

Schematic diagram shows PENETRON® application only and does not depict the standard requirements for waterstops or expansion joint sealant.