



- ❶ Joints waterproofing: According to Construction Joint Detail – Walls or Slabs.
- ❷ Immersed tube waterproofing: Apply PENETRON® on the positive surface of sidewall and top slab as indicated in 2 coats at $1.4\text{--}1.6\text{ kg/m}^2$ ($2.5\text{--}3.0\text{ lbs/y}^2$) in total.

Notes: Schematic diagram shows PENETRON® application only and does not depict the standard requirements for waterstops or expansion joint sealant.