



- 1 Joints waterproofing: Clean joint thoroughly. Between pours, apply PENETRON® slurry to joint surfaces at 1.4-1.6 kg/m² (2.5-3.0 lbs/y²).
- 2 Strips sealing: Clean pre-formed reglet thoroughly. Apply one slurry coat of PENETRON® to reglet at the rate of 0.8 kg/m² (1.5 lbs/y²). Fill reglet with PENECECRETE™ in mortar consistency. Pre-formed reglet may be offset to either side of joint.
- 3 PENETRON® slurry application: Coat the entire repair area with PENETRON® slurry extending 250mm (10in) beyond either side of the repair.

Notes:

- Waterproofing concrete should be poured as continuously as possible.
- Schematic diagram shows PENETRON® application only and does not depict the standard requirements for waterstops or expansion joint sealant.