

JAZ-DECOTIVE JA-15001

DESCRIPTION:

A high quality matt finish emulsion paint based on acrylic emulsion for interior applications. It provides very good application properties.

RECOMMENDED USE:

Recommended to use as a finish coat on concrete, cement, gypsum, hard board and brick surfaces for interior applications

CHARACTERISTICS:

- "Jaz-Decotive" has the following features:
- Excellent adhesion property.
- Provides very smooth flat finish.
- Excellent hiding property.
- Very Low VOC (Volatile Organic Components).
- Formaldehyde free.
- APEO free.
- Ammonia free.

CERTIFICATES:

- In accordance with the SASO standard No.: 470 / 2002.
- Tested and approved by Dortmund University of VOC contents.
- Certificated by Green Seal.
- Meets U.S. Green Building Council's LEED® Standards Environmental Sustainability according to Green Seal (GS-11) approval.
- Meets MPI standard # 143

PHYSICAL CONSTANTS:

Finish: Matt.

Colour: Produced in white and other colours

as per Al-Jazeera Colour card.

Specific Gravity: 1.54 at temperature of 25°C. ASTM

D1475.

Viscosity: 112 KU at temperature of 25°C.

ASTM D562.

Volume Solid: 41.50 %. ASTM D2697.

D.F.T.: 40 μ each coat.

Theoretical

Spreading Rate: 6.7 m²/Kg (416 ft²/ US gallon) at

D.F.T. 40 μ .(to avoid waste, be sure to buy the right amount of the paint for the surface area required).

Hiding: Above 95 % at W.F.T 100 μ . D2805

Sagging: 200μ , ASTM D4400.

Scrub Resistance: Above 2000 cycles, ASTM D 2486

Abrasive scrub medium by Nylon

Brush

Water Resistance: Pass, 7 days, ASTM D 870

Alkali Resistance: Pass, 7 days (1 % solution), ASTM

D1308

Salt Resistance: Pass, 7 days (1.5 % solution), ASTM

D1308.

Adhesion: Pass, ASTM D3359 -2

Flexibility: Pass, 6 mm. Diameter, ASTM D522
Freeze-Thaw Stability Pass, 3 cycles, ASTM D 2243.
Heater Stability: Pass, 30 days at 52°C. ASTM D 1849
VOC: 3.1g/ltr* (@ 280°C) ASTM D6886).

SURFACE PREPARATION

New surfaces

- All new surfaces must be cured at least for 30 days prior to application of the primer.
- The surface must be treated by removing all forms release and protrusions to get a suitable surface for application.
- For previously painted surfaces:
- Remove old paint from surfaces completely.
- Make sure that the surface is clean , dry , free from dust, oil, grease, salt and mold.
- Fill the holes and cracks with suitable fillers "Al-Jazeera Crack Filler" prior to application of the primer.

APPLICATION GUIDE:

- 1. The surface must be removed from dust, grease, oil and other contaminants completely.
- Surface temperature required during application must not be less than 10°C; the surface moisture should not exceed 8% and the relative humidity at work place not to exceed 70%.
- 3. Maximum pH of 9.
- 4. Paint should be stirred carefully before use.
- 5. A suitable quantity of water can be added to get reason able viscosity for application.
- Do not apply on wet and moistened surfaces until get completely dry.
- Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be given between the two coats.
- Adequate ventilation should be provided during drying time.

APPLICATION TOOLS:

•Airless spray: Larius - Excalibur

Nozzle orifice : 0.017-0.021" Nozzle pressure : 15 MPa (2100psi)

Spray angle : 40-80°

•Spray gun : Recommended nozzle size: (1.5 – 1.8)mm. •Roller: Recommended Type:Soft and smooth woolenroller.

•Brush.:General / Normal type.

THINNER:

Recommended thinner is "Tap Water".

THINNING RATIO:

- (0 10)% by volume for airless spray gun applications.
- (20 30)% by volume for spray gun applications.
- (10 20)% by volume for roller & brush applications. Depends on the weather conditions at work place.

PAINTING SYSTEM:

- Apply one coat of "Al-Jazeera Primex" or any other suitable type of Al-Jazeera primers and leave for full dry.
- Apply two coats of "Al-Jazeera Easy Putty" then sand the surfaces with sanding paper and clean the dust coming from the sanding by a dry cloth or an air blower.
- Apply two coats of "Jaz-Decotive".

*Test report available on request.

Disclaimer

Issued 2013 **–**

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Al-Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Al-Jazeera TSD, he should take his accountability in this connection.





JA-15001 JAZ-DECOTIVE

DRYING TIME:

- Surface dry 30 minutes. - Full dry 2 hours.

- Recoating interval 4 hours.(minimum)

All above results according to ASTM D5895@25°C.

CLEANING TOOLS:

Tap water.

PACKING:

US Gallon. 28 Kg. Drum.

3 Ltr.(Tint able Base by coloring machine). Gallon: Base Drum: Base 17 Ltr.(Tint able Base by coloring machine).

SHELF LIFE:

In sealed container: 12 months in a dry, cool and well-ventilated place.

SAFETY PRECAUTIONS:

During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided. When working with paint in in-sufficient ventilated areas, forced ventilation should be provided. For spray application system, eye, skin, respiratory protection are always recommended. Keep away from the reach of

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

*Test report available on request.